



PRODUCT DATA SHEET

WCD 6109

HYDROGEN CONTROLLED ELECTRODES

AUSTARC 16TC



SUMMARY

- > Basic/Twin Coated (TC) Manual Arc Electrode
- > Versatile/All Positional (Especially Vertical Up) Capabilities
- > Reliable, Low Temperature Impact Toughness
- > Easy to Strike and Re-Strike
- > Smooth Performance on Low OCV AC Welding Machines

IDENTIFICATION

Coating - Light Grey **Tip** - Bronze **Imprint** - WIA 4916A

CLASSIFICATION

- > AS/NZS 4855-B - E49 16-A U H10
- > AWS A5. 1: E7016-1 H8

DESCRIPTION AND APPLICATION

Smooth running, basic low hydrogen electrode, developed for all positional (except vertical down) welding, using AC or DC power sources. It has exceptional arc stability and weldability and delivers high quality weld deposits with reliable notch toughness to -40 °C. Austarc 16TC is manufactured using a unique twin coating extrusion process, which means all the arc stabilising elements are concentrated in the inner coating. This delivers significantly improved arc stability and control for all applications.

OPERATIONAL DATA

ELECTRODE SIZE (MM)	ELECTRODE LENGTH (MM)	WELDING CURRENT RANGE *(A)
2.5	300	60 - 90
3.2	380	90 - 135
4.0	380	140 - 190
5.0	450	190 - 240
6.0	450	250 - 310

*Please note, 2.5 and 3.2 Austarc 16TC are recommended for DC+ or AC (minimum 45 OCV) operation, whereas 4.0, 5.0 and 6.0mm sizes require a minimum of 55 OCV for stable AC operation.

SHIPPING APPROVAL

LRS 4Ym H10 **ABS 3 H10** **DNV 3Y H10**

TYPICAL ALL WELD METAL CHEMICAL ANALYSIS

C	Mn	Si	P	S	Fe
0.06	1.2	0.4	0.015	0.010	Bal

TYPICAL ALL WELD METAL MECHANICAL ANALYSIS

Yield Strength	460 MPa
Tensile Strength	560 MPa
Elongation	28%
CVN Impact Values	130J @ -20 °C 110J @ -40 °C

PACKAGING DATA

ELECTRODE SIZE (MM)	PACKAGING (KG)		APPROX. NO. OF RODS PER KG	PART NO.
	PACKET	CARTON		
2.5	2.5	12.5	61	16TC25
3.2	5.0	15	29	16TC32
4.0	5.0	15	19	16TC40
5.0	5.0	15	10	16TC50
6.0	5.0	15	7	16TC60

MATERIALS TO BE WELDED

	CODE	TYPE
Structural Steel	AS 1163	C250, C350, C450
	AS 1397	G250, G300, G350, G450
	AS 1450	C/H200, C/H250, C/H350, C/H450
	AS/NZS 3679.1	250, 300, 350, 400
	AS/NZS 3678.1 AS/NZS3679.2	200, 250, 300, 350, 400, 450, A1006, XK1016, WR350
Pressure Equipment Steel	AS 1548	7-430, 7-460, 5-590, 7-490
Fine Grain Steel	AS/NZS 1594	HAI, HA3, HA4N, HA200, HA250, HA300, HA1006, HA1010, HA1016, HA350, HA400
Cast Steel	AS/NZS 1594	HAI, HA3, HA4N, HA200, HA250, HA300, HA1006, HA1010, HA1016, HA350, HA400
Pipe Material	API 5LX	X42, X46, X52, X60

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Welding Industries of Australia expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with the AWS and or AS/NZS specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique by Welding Industries of Australia.

Issue CA - 1st February 2013



welding.com.au 1300 300 884