

PRODUCT DATA SHEET

IRON POWER ELECTRODES

AUSTARC 24

SUMMARY

- > High Iron Powder, Rutile Type Electrode
- > High Deposition Rates and Efficiencies
- > Suitable for Fast Downhand Fillet and Butt Welding

IDENTIFICATION

Coating - Brown Tip - Yellow Imprint - WIA 4924A

CLASSIFICATION

- > AS/NZS 4855-B E49 24 A
- > AWS A5.1: E7024

DESCRIPTION AND APPLICATION

Austarc 24 is a high iron powder, rutile type electrode designed for the fast down hand welding of mild steel using AC or DC power sources. Features include high deposition rates/efficiencies and flat to slightly concave fillet welds with excellent "edge wash" and slag detachability. With its smooth running, positive re strike and high current carrying capacity, Austarc 24 is the ideal fillet welding electrode for down hand positions aimed at higher productivity.

Austarc 24 is suited to long, heavy fillet and butt welding applications using a touch welding or `short arc' technique. Such applications include the production welding of tanks, structural members/frames and truck and tractor bodies etc.

OPERATIONAL DATA

ELECTRODE SIZE (MM)	ELECTRODE LENGTH (MM)	WELDING CURRENT RANGE *(A)	ARC VOLTAGE RANGE **(V)
3.2	380	120 - 170	24
4.0	450	200 - 240	25
5.0	450	270 - 320	26

*Recommended for DC +/- or AC (minimum 55 OCV) operation. **Voltage is determined by arc current and electrode arc length. Arc voltage shown is typical and is only to be used as a guide.

SHIPPING APPROVAL

LRS 2Ym ABS 2 DNV 2

TYPICAL ALL WELD METAL CHEMICAL ANALYSIS

С	Mn	Si	Fe
0.06	0.7	0.4	Bal

TYPICAL ALL WELD METAL MECHANICAL ANALYSIS

Yield Strength	416 MPa
Tensile Strength	510 MPa
Elongation	32%
CVN Impact Values	60J @ -0°C

PACKAGING DATA

ELECTRODE SIZE (MM)	PACKAGING (KG)		APPROX. NO. OF RODS PER KG	PART NO.
	PACKET	CARTON		
3.2	5.0	15	18	2432
4.0	5.0	15	12	2440
5.0	5.0	15	6	2450

The information contained or otherwise referenced herein is presented only as "typical" without guarantee or warranty, and Welding Industries of Australia expressly disclaims any liability incurred from any reliance thereon. Typical data is obtained when welded and tested in accordance with the AWS and or AS/NZS specification. Other tests and procedures may produce different results. No data is to be construed as a recommendation for any welding condition or technique by Welding Industries of Australia.

Issue CA - 1st February 2013

