



**PRODUCT SPECIFICATIONS**  
**ULTRALOC®**  
**ADHESIVES &**  
**SEALANTS**

**ULTRALOC® 3262**

**Anaerobic Thread Locking Compound**

ULTRALOC 3262 is a fast curing, medium to high strength anaerobic thread locking compound for bonding and sealing threads, and retaining of cylindrical parts. It is highly resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

**Applications:**

- Ideal for thread locking heavy duty applications such as bolts used in transmission, construction equipment or railroad assemblies, etc.
- Lubricated for easy assembly. Prevents loosening and leakage of threaded fasteners. Locks and seals threaded joints-nuts, screws, and studs.
- Meets 90% of all nut and bolt thread locking applications.
- Meets military specification: MIL-S-46163A Type II Grade O

**Physical Properties:**

Composition:	Methacrylate
Ester	
Color:	Red
Viscosity @ 25°C, mPa.s (cp) Brookfield Spindle 3 @ 2 rpm:	5,000 cps
@ 20 rpm:	1,800 cps
Specific Gravity:	1.1
Flash Point:	> 95°C
Solvent Content:	None
Shelf Life:	1 year

**Curing Properties:**

Handling Cure Time:	10-20 mins
Functional Cure Time:	1-3 hours
Full Cure Time:	24 hours
Shear Strength:	8 - 12 N/mm <sup>2</sup>
Locking Torque	
--Break	17 - 29 N.m
--Prevailing	17 - 46 N.m
Breakloose Torque	25 - 50 N.m.
--Temperature Range	-55 to 150 °C

**Chemical Resistance:**

Chemical	Temp.	% Initial Strength Retained	
		500 hours	1000 hours
Acetone	22 °C	100	90
Ethanol	22 °C	100	100
Motor Oil	125 °C	100	100
Gasoline	22 °C	100	100
Brake Fluid	22 °C	100	100
Water/Glycol	87 °C	90	80

**Application Method:**

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. ULTRALOC 3262 performs the best in thin bond gaps. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

**Storage:**

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 10°C to 22°C. Please do not return any unused material to its original container.

**Packaging:**

10ml P/No 326210      50ml P/No 326250      250ml P/No 326225

**MOLYTEC AUSTRALIA P/L**  
**P.O. Box 5357 Alexandra Hills Q4161**  
**1/9 Steel St Capalaba Q 4157**  
**Tele: 07 32452355 Fax: 07 32452499**  
**e-mail: [molytec@bigpond.net.au](mailto:molytec@bigpond.net.au)**  
**web : [molytec.com.au](http://molytec.com.au)**

**PRECAUTIONS:** This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

**Warranty:** All products purchased from or supplied by Molytec Australia are subject to terms and conditions set out in the contract. Molytec Australia warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Molytec Australia is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Molytec Australia makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.