



PRODUCT SPECIFICATIONS
ULTRALOC®
ADHESIVES &
SEALANTS

ULTRALOC® 3294

Anaerobic Thread Locking Compound

ULTRALOC 3294 is a fast curing, penetrating, medium to high strength anaerobic thread locking compound for bonding and sealing threaded fasteners. The product also provides good threadlocker performance with oil-coated fasteners. It is highly resistance to heat, vibrations, water, gases, oils, hydrocarbons and many chemicals.

Applications:

- Penetrates threads by capillary action. Medium to high strength threadlocker.
- Ideal for sealing hairline cracks, small nuts and bolts.
- Seals and welds porous metal parts. Localize heating and hand tools are needed for disassembly. Prevents corrosion and leakage.
- Secure setscrews and other assemblies after settings are completed.
- Fasteners on vibrating machines or moving components.

Physical Properties:

Composition: Methacrylate Ester
Color: Green
Viscosity: 20 - 45 cps at 25 °C
Brookfield-LVF spindle 2 @ 50 rpm
Specific Gravity: 1.11
Maximum Diameter of Thread/Gap Filling: M 5/ 1/2 " / 0.07 mm
Flash Point: > 100 °C
Solvent Content: None
Shelf Life: 1 year

Curing Properties:

Handling Cure Time: 10-20 minutes
Functional Cure Time: 1-3 hours
Full Cure Time: 24 hours
Shear Strength: 8 - 12 N/mm²
Locking Torque
--Break 30 - 35 N.m
--Prevailing 25 - 30 N.m
--Temperature Range -55 to 200 °C

Chemical Resistance:

Chemical	Temp.	% Initial Strength Retained	
Acetone	22 °C	500 hours	1000 hours
Ethanol	22 °C	100	97
Motor Oil	125 °C	100	100
Gasoline	125 °C	67	65
Brake Fluid	22 °C	100	100
Water/Glycol	22 °C	100	100
	87 °C	75	70

Application Method:

Surfaces should be dry, clean, and free of any contamination. Thread locker should be applied to the bolt in sufficient quantity to fill threads. ULTRALOC 3294 performs the best in thin bond gaps. This thread locker is specifically formulated to give controlled friction and torque/tension ratio during assembly.

Storage:

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 10 °C to 22 °C Please do not return any unused material to its original container.

PACKAGING:

10ml P/No 329410 50ml P/No 329450 250ml P/No 329425

MOLYTEC AUSTRALIA P/L
P.O. Box 5357 Alexandra Hills Q4161
1/9 Steel St Capalaba Q 4157
Tele: 07 32452355 Fax: 07 32452499
e-mail: molytec@bigpond.net.au
web : molytec.com.au

PRECAUTIONS: This product and the auxiliary materials normally combined with it are capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

Warranty: All products purchased from or supplied by Molytec Australia are subject to terms and conditions set out in the contract. Molytec Australia warrants only that its product will meet those specifications designated as such herein or in other publications. All other information supplied by Molytec Australia is considered accurate but are furnished upon the express condition the customer shall make its own assessment to determine the product's suitability for a particular purpose. Molytec Australia makes no other warranty, either express or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or product will nor infringe any patent.