

### Key Facts

- Premium 10% si double shaved tig/oxy wire
- Very low oxide levels resulting in superior welds
- Can be used as a substitute for 4043 wires to increase silicon in the weld metal, minimize hot cracking and produce higher fillet weld shear strength

### Description

An aluminium alloy rod containing 10% silicon to produce higher weld sheer strength and minimise hot cracking. The slightly lower melting point and higher fluidity of 4047 make it ideal for brazing operations.

### Classifications, Approvals & Conformances

A5.10 ER4047

### Applications

Used to braze aluminium alloy sheets, extruded shapes and castings. Suitable to use when welding aluminium structures, for example aircraft, vehicles, boats and aluminium alloy furniture.

- Oxy and tig applications
- Automotive repairs
- Aluminium extrusions
- Heat exchangers
- Excellent maintenance wire

### Recommended Shielding Gas

100% Argon Argon / Helium Mixtures Flow Rate: 30 - 50 CFH

### Welding Positions

All positions

### Typical Wire Analysis

Cu - Copper	Mn - Manganese	Si - Silicon	Others
< 0.30	< 0.15	11.0 – 13.0	< 0.15
Zn - Zinc	Fe - Iron	Mg - Magnesium	Al - Aluminium
< 0.20	< 0.80	< 0.10	Balance

### Typical Weld Mechanical Properties

<b>Yield Strength:</b>	60 MPa
<b>Tensile Strength:</b>	130 MPa
<b>Elongation:</b>	5%

### Packaging & Ordering Information

Size	Packet	Part Number
2.4mm	1kg	300030H
3.2mm	1kg	300031H
4.8mm	1kg	300032H

Disclaimer: The above information is provided as a guide; actual welding current and voltage will depend on the welding machine characteristics, which will vary from model to model. Other variables include run length and size, plate thickness, operator technique and gas type (if used). The user must evaluate the process, application and recommended professional advice. Under no circumstance will Dynaweld or its affiliates be liable for misuse or application of products this is entirely up to the user's ability.