



A NEW FORCE IN CHEMICAL MANUFACTURING

Unit 2, 14-16 Lee Holm Road
St Marys NSW 2760
Australia

Ph: 1300 738 250 (Australia)
Ph: +61 2 9833 9766 (International)
Fax: 02 9623 3670

sales@chemtools.com.au
www.chemtools.com.au

TECHNICAL DATA SHEET

SEPTEMBER 2014

PRODUCT NAME

8609 Fast Curing, Medium Strength Anaerobic Retaining Compound

PRODUCT RANGE

| Part Number | Available Size |
|-------------|----------------|
| 8609-10 | 10 ml |
| 8609-50 | 50 ml |
| 8609-250 | 250 ml |



Refer to MSDS for product safety guidelines

8609 Fast Curing, Medium Strength Anaerobic Retaining Compound

Chemtools® 8609 is a fast curing, medium strength anaerobic retaining compound for continuous working temperatures up to 150°C. It is ideal for gap distances up to 0.127 mm diameter.

APPLICATIONS:

- Joining rotor to shafts in fractional and sub-fractional horsepower motors.
- High temperature resistance retaining compound.
- Used for close fitting parts, rotor on shafts, bushes, pulleys and gears.
- Excellent retaining, sealing and thread locking compound.
- Meets US Military Specification R - 46082B Type I.

ADHESIVE PROPERTIES:

| | |
|---|--------------------|
| Composition | Methacrylate Ester |
| Appearance | Green |
| Viscosity @ 25°C (Brookfield RVT, Spindle 4 @ 20 rpm) | 125 cps |
| Specific Gravity | 1.10 |
| Flash Point | > 100°C |
| Solvent Content | None |
| Shelf Life | 1 Year |

CURING PROPERTIES:

| | |
|----------------------|-------------|
| Handling Cure Time | 10 minutes |
| Functional Cure Time | 1 - 3 hours |
| Full Cure Time | 24 hours |

Compressive Shear Strength - ISO 10123

| | |
|---|---------------------------------------|
| After 24 hours at 22°C (Steel Pins and Collars) | 17 - 19 N/mm ² (3,125 psi) |
| After 30 minutes at 22°C (Steel Pins and Collars) | 13 - 15 N/mm ² (1,960 psi) |
| Temperature Range | -55 to 150°C |

PHYSICAL PROPERTIES:

| | |
|--|-----------------------|
| Coefficient of Thermal Conductivity, ASTM C177, W/m.K | 0.10 |
| Coefficient of Thermal Expansion, ASTM D696, K ⁻¹ | 80 x 10 ⁻⁶ |
| Specific Heat, kJ/kg.K | 0.30 |

CHEMICAL RESISTANCE PROPERTIES:

| Chemical | Temperature | % Initial Strength Retained | |
|--------------|-------------|-----------------------------|------------|
| | | 500 hours | 1000 hours |
| Acetone | 22°C | 100 | 90 |
| Ethanol | 22°C | 100 | 100 |
| Motor Oil | 125°C | 100 | 100 |
| Petrol | 22°C | 100 | 100 |
| Brake Fluid | 22°C | 100 | 100 |
| Water/Glycol | 87°C | 90 | 80 |

APPLICATION INSTRUCTIONS:

For Assembly

- For best results, clean all surfaces (external and internal) with a cleaning solvent and allow solvent to evaporate.
- If the material is an inactive metal or the cure speed is too slow, spray with Activator 8071 or 8049 and allow drying.
- For Slip Fitted Assemblies, apply adhesive around the leading edge of the pin and the inside of the collar and use a rotating motion during assembly to ensure good coverage.
- For Press Fitted Assemblies, apply adhesive thoroughly to both bond surfaces and assemble at high press on rates.
- For Shrink Fitted Assemblies, the adhesive should be coated onto the pin, the collar should then be heated to create sufficient clearance for free assembly.
- Parts should not be disturbed until sufficient handling strength is achieved.

For Disassembly

- Apply localised heat to the assembly to approximately 250°C. Disassemble while hot.

STORAGE:

Anaerobic adhesives shall be ideally stored in a cool, dry place in unopened containers at a room temperature between 7°C to 28°C. Please do not return any unused material to its original container.

PRECAUTIONS:

This product is capable of producing adverse health effects ranging from minor skin irritation to serious systemic effects. None of these materials should be used, stored, or transported until the handling precautions and recommendations as stated in the Material Safety Data Sheets (MSDS) for this and all other products being used are understood by all persons who will work with the material.

WARRANTY:

All products purchased from or supplied by Chemtools® are subject to terms and conditions set out in the contract. Chemtools® warrants only that its products meet the specifications designated as such herein, or in other publications. All other information supplied by Chemtools® is considered accurate, but is furnished upon the express condition. The customer shall make its own assessment to determine the products suitability for a particular purpose. Chemtools® makes no other warranty, either expressed or implied, including those regarding such other information, the data upon which the same is based, or the results to be obtained from the use thereof; that any product shall be merchantable or fit for any particular purpose; or that the use of such other information or products will not infringe any patent.